



Product Data Sheet

Transpoxy EC Coating 3.62

Product description.

A two pack polyamide cured high build recoatable epoxy topcoat for interior and exterior use. Good resistance against water and spillage of mild solvents and chemicals. Transpoxy EC Coating cures to a tough and flexible coating and provides excellent adhesion to Transpoxy priming systems.

Physical properties.

Colour / Texture White, AS2700 Colours / Gloss
 Volume Solids Dependent on colour shade, approx. 62 %
 Specific gravity Dependent on colour shade, approx. 1.3 gr/ml
 VOC Dependent on colour shade, approx. 337gr/litre
 Flashpoint >25 °C

	Dry film thickness per coat (μ)	Wet film thickness per coat (μ)	Theoretical spreading rate (m ² /l)
Range	75 – 150	120 – 245	8.2 – 4.1
Recommended	100	160	6.2

Application data.

Mixing ratio By volume, base to hardener: 4:1

Pot-life 10 °C: 8 hours, 23 °C: 6 hours, 30 °C: 4 hours.

Guiding data - Airless spray Pressure at nozzle: 120 - 180 bar. Nozzle size: 0.38 - 0.53 mm.
 Spray angle: 40 - 80 degrees.
 Volume of thinner: 0 - 3%.

Guiding data - Air spray Pressure: 3 - 5 bar. Nozzle size: 1.2 - 2.0 mm.
 Volume of thinner: 0 - 5%.

Brush / Roller Suitable.
 Volume of thinner: 0 - 5%.

Thinner / Cleaner Transocean Epoxy Thinner 6.03.
 If thinning is necessary, this should be added after mixing of the two Components. Avoid excessive thinning as it will result in lower sag resistance and slower cure.

Drying and recoating times.

Substrate temperature	Touch dry	Dry to handle	Full cure	Dry to recoat	
				Minimum	Maximum (2)
10 °C	4 hours	8 hours	6 days	12 hours	Indefinite
23 °C	2 hours	6 hours	4 days	8 hours	Indefinite
30 °C	1 hours	4 hours	3 days	6 hours	Indefinite

(1) The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, preceding paint system etc

(1) The surface should be dry and free from contaminants prior to overcoating. The best intercoat adhesion is achieved when the subsequent coat is applied before the preceding coat is fully cured. When in doubt, consult your nearest Transocean office.

Surface preparation.

Coated substrates Existing systems should be dry and free from loose paint, salt, grease and other contaminants prior to overcoating.
Oil and grease should be removed by solvent cleaning according to SSPC-SP1.
Remove salts and dirt by fresh water washing.
Corroded areas should be repaired first with an appropriate primer system.

Recommended paint system.

Transpoxy Finish can be applied on Transpoxy priming systems. A typical system for atmospheric exposure is shown below.

Transpoxy EC Primer 1.42	1 x 75 μ dft.
Transpoxy EC Coating 3.62	1 x 100 μ dft.
Transurethane Finish 3.43	1 x 50 μ dft.

Application conditions.

The temperature of the substrate should be at least 3°C above the dew point of the air. Temperature and relative humidity should be measured in the vicinity of the substrate.
The maximum recommended surface temperature is approx. 40°C. Higher steel temperatures are acceptable provided dry-spray is avoided by proper spray application and extra thinning if required. In extreme cases it may be necessary to reduce film thickness in order to avoid sagging.
When applying the paint in confined spaces, provide adequate ventilation during application and drying.
The temperature of the mixed paint should be at least 15°C, otherwise extra solvent may be required to obtain a proper application viscosity.

Storage and shelf life.

The product must be stored in accordance with national regulations. The cans are to be kept in a dry, cool, well ventilated space and away from source of heat and ignition. Cans must be kept tightly closed.

Worldwide availability

The product is part of the common Transocean product range but local availability is subject to confirmation. Although we strive to supply the same product through the world, slight modifications of the product in some cases may be necessary in order to comply with local conditions and/or national regulations. In such cases an alternative datasheet will be issued.

Health and safety.

Observe the precautionary notices on the label of the container. A material safety data sheet is available upon request and national or local safety regulations should be followed. This product is intended for use by professional applicators.

As a general rule, avoid skin- and eye contact by wearing overalls, gloves, goggles, mask, etc. Spraying should be carried out under well-ventilated conditions. This product contains flammable materials and should be kept away from sparks and open flames. Smoking in the area should not be permitted.

Disclaimer

The information in this data sheet is provided to the best of our knowledge. However, we have no control over either quality or condition of the substrate and other factors affecting the use and application of this product. Therefore, we cannot accept any liability whatsoever or howsoever arising from the performance of the product or for any loss or damage arising from the use of this product. We reserve the right to change the product without notice.

Date of issue: July, 12.