



T1 Polyurethane Spray Thinner

Code: THT10000

Description

- Blended thinner for reducing 2K polyurethanes to spray viscosity

Properties

- Fast initial flash-off for better vertical hold up
- Flow out properties to enhance gloss

Typical Applications

- Thinning of Rhinothane[®] T and Rhinothane[®] AC

General Data

- Specially formulated blend of hydrocarbon and chemical solvents

Specifications (at 25°C and 50% relative humidity)

- Appearance..... Low viscosity, clear, water-white liquid
- Specific Gravity.....0.88
- Boiling Range..... 80 - 170°C

Mixing recommendation

- Rhinothane[®] T 5-10% by volume on mixed Part A and Part B
- Rhinothane[®] AC up to 20% by volume on mixed Part A and Part B

Safety precautions

- **Refer to the relevant Material Safety Data Sheet**
- Contents are flammable – keep away from all ignition sources
- Avoid contact with skin and eyes – when mixing, wear gloves and goggles
- When spraying, ensure adequate ventilation and wear appropriate protective clothing and equipment

Packaging Group II UN No. 1263

Pack sizes 1 litre, 4 litre, 20 litre, 60 litre

Authorised: A. De Mello, Sales Manager

June 2008

These technical data and recommendations are based on tests and information believed to be accurate at the time of printing. They should not be construed as containing any warranty, either expressed or implied. Users should conduct their own tests to determine final suitability of this product.



Wagon Paints

5 Stephenson Road, Bayswater North, Victoria 3153 Australia
Phone: 61 3 97291344 Fax: 61 3 97202179 Email: sales@wagonpaints.com.au